

LGAI Technological Center, S.A. (APPLUS) Campus UAB Ronda de la Font del Carme, s/n E - 08193 Bellaterra (Barcelona) T +34 93 567 20 00 F +34 93 567 20 01 www.appluslaboratories.com



E/F

CLASSIFICATION OF REACTION TO FIRE IN ACCORDANCE WITH UNE-EN 13501-1:2019

		Page 1 of 5
Sponsor:	TOPCRET Gran Vía de les Corts Catalanes, 828 08013 Barcelona	
Prepared by:	LGAI Technological Center, S.A. (APPLUS) Campus UAB Ronda de la Font del Carme, s/n E - 08193 Bellaterra (Barcelona)	
Product name:	Baxab NF	
Classification report no:	19/21115-2710-2 English Version	
Date of issue:	14 th April, 2020	

1.-INTRODUCTION

This classification report defines the classification assigned to "Baxab NF" in accordance with the procedures given in the UNE-EN 13501-1:2019 standard.

2.- DETAILS OF CLASSIFIED PRODUCT

2.1.-General

The product "Baxab NF" is defined as two-component polymeric cementitious material according to petitioner.

This document may only be copied in full. Digital reports with an electronic signature will be considered as an original document, as well as its respective electronic copies. The impression of this document will not have legal validity. This document has 5 pages, of which -- are annexes. LGAI, Technological Center, S.A. is not responsible for the documentation and/or information provided by the petitioner.



File nº 20/21115-2710-2

Page 2 of 5

2.2.-Product description

In accordance with the technical specifications provided by the petitioner:

Product trade name: Baxab NF

Two-component polymeric cementitious material.

The product is composed by four layers:

- -Layer 1: Microcement base, thickness of 1 mm, superficial density of 1,8 kg/m², cement-grey colour and rough appearance.
- -Layer 2: Baxab, thickness of 0,40 mm, superficial density of 0,64 kg/m², colour to choose and rough appearance.
- Layer 3: Baxab NF, thickness of 0,30 mm, superficial density of 0,54 kg/m², colour to choose and smooth appearance.
- -Layer 4: Shielding, thickness of 0,1 mm and superficial density of 0,1 kg/m².
- -Layer 5: Mesh, thickness of 0,2 mm, superficial density of 90 g/m², white colour and mesh appearance.

The petitioner did not provided more information.

Fixing system: The test was carried out with product applied onto the substrate (Calcium Silicate board according to standard UNE-EN 13238:2011) by the petitioner.

Manufacturer: TOPCRET, Gran vía de les Corts Catalanes, 828, 08013 Barcelona.

3.-REPORT AND RESULTS IN SUPPORT OF THIS CLASSIFICATION

3.1- Reports

Name of Laboratory	Name of sponsor	Report ref. no.	Test method and date
Applus – LGAI	TOPODET	TOPCRET 19/21115-2708-1	UNE-EN ISO 11925-2:2011 19-03-2020
	TOPCRET		UNE-EN 13823:2012+A1:2016 11-03-2020



Page 3 of 5

3.2- Results of the Tests

Test Mode	RESULTS – Baxab NF					
Test Mode	CRITERIA CLASS B Nº TES		AVERAGE	COMPLIANCE		
UNE-EN-ISO 11925-	WITHIN 60 S		F₅<150 mm	YES		
2:2011	Paper inflammation		NO	YES		
	$FIGRA_{0.2 MJ} \le 120 W/s$	3	93,62	YES		
	LFS $<$ edge of the sample	3	<to edge<="" td=""><td>YES</td></to>	YES		
	THR _{600s} ≤ 7,5 MJ	3	0,80	YES		
UNE-EN	CRITERIA subclass `s1'	Nº TESTS	AVERAGE	COMPLIANCE		
13823:2012+A1:2016	SMOGRA \leq 30 m ² /s ²	3	4,74	YES		
	$TSP_{600s} \leq 50 m^2$	3	27,01	YES		
	CRITERIA subclass 'd0'	Nº TESTS	AVERAGE	COMPLIANCE		
	Fall of droplets/particles in flames within 600 s	3	NO	YES		

4.- CLASSIFICATION AND FIELD OF APPLICATION

4.1- Reference of classification

This classification has been carried out in accordance with UNE-EN 13501-1:2019: "Classification in terms of the behaviour to fire of construction products and building elements. Part 1: Classification made from the data gathered during fire reaction tests".

4.2- Classification

The product, Baxab NF, in relation to its reaction to fire behaviour is classified:

В

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0



Fire Behaviour		Sm	oke Production		Flam	ing droplets
В	-	S	1	,	d	0

REACTION TO FIRE CLASSIFICATION : B-s1,d0

This classification is only valid for the final conditions of use described in the present report.

4.3- Field of application

• This classification is valid for the following product parameters:

The classification is only valid for the product characteristics shown, with the following parameters being extended:

- Variable parameter 1: SUBSTRATE

After performing the test with the product adhered on calcium silicate substrate with $(870\pm50) \text{ kg/m}^3$ in density, $(11\pm2) \text{ mm}$ in thickness, the obtained results are valid for substrates of final use of the classes A1 and A2-s1,d0, according to standard UNE-EN 13238:2011.

• The classification is valid for the following final use applications:

Wall covering.



Substrate	Calcium Silicate board (UNE-EN 13238:2011)
Fixing method	Applied
Joints	No
Air gap	Non ventilated
Others	-

5.- LIMITATIONS

This classification document does not represent type approval or certification of the product.

Responsible of the Fire Laboratory LGAI Technological Center S.A. (APPLUS) Responsible Technician of Reaction to Fire LGAI Technological Center S.A. (APPLUS)

The results refer exclusively to the samples tested at the time and under the conditions indicated. Under customer request, the decision rule agreed to give conformity declaration with the classification standard, is to comply when the result of the measeure, whitout taking into account the uncertainty value associated with the test, does not exceed the specification limit.

Applus+ guarantees that this task has been carried out in compliance with the requirements of our Quality and Sustainability System, and furthermore, that the contractual terms and legal regulations have been complied with. In the framework of our improvement programme, we would appreciate any comments you may deem appropriate. These should be addressed to the manager who signs this document, or to the Quality Director of Applus+, at the following address:<u>satisfaccion.cliente@applus.com</u>

In the event of litigation, the Spanish version will be valid